

CLAIMS

5 What is claimed is:

10 1. A specialty fluoroelastomer comprising copolymerized units of
45 to 80 weight percent tetrafluoroethylene; 10 to 40 weight percent
propylene; and 0.1 to 15 weight percent of 3,3,3-trifluoropropene-1 cure
site monomer.

15 2. A specialty fluoroelastomer of Claim 1 wherein said
copolymerized units of tetrafluoroethylene are present in an amount
between 65 and 78 weight percent; said copolymerized units of propylene
in an amount between 15 and 25 weight percent; and said copolymerized
units of 3,3,3-trifluoropropene-1 cure site monomer in an amount between
2 and 10 weight percent.

20 3. A specialty fluoroelastomer of Claim 2 further comprising
copolymerized units of vinylidene fluoride present in an amount between 2
and 20 weight percent.